



CLAYBURN INDUSTRIES LTD.

33765 PINE STREET
ABBOTSFORD, BC
CANADA V2S 5C1
PHONE: (604) 859-5288
FAX: (604) 859-0424

TECHNICAL DATA

CLAYBURN CAST FSLC/AL

CLAYBURN CAST FSLC/AL is a low cement, thermal shock resistant castable containing a high percentage of fused silica. It was developed specifically for aluminum contact applications. CLAYBURN CAST FSLC/AL is ideal for precast shapes or for the original lining for tapholes and filter boxes.

SERVICE TEMPERATURE:	2200°F
MATERIAL REQUIRED FOR ESTIMATING:	118 lbs./cu. ft.
CASTING WATER:	approx 5%

TYPICAL CHEMICAL ANALYSIS
(Calcined Basis)

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	MgO	CaO	Alkalies	Other
14.7	78.9	0.1	Nil	0.1	3.2	0.1	2.9

TYPICAL PHYSICAL PROPERTIES

Prefired to °F	Modulus of Rupture, psi	Cold Crushing Strength, psi	Linear Change %
250	2020	6310	-0.1
1000	1540	9640	-
1500	1440	-	-0.3

APP. POROSITY: 12.6% After 1500°F

165420 – 04/11/02

**ALL DATA SUBJECT TO REASONABLE DEVIATION AND THEREFORE
SHOULD NOT BE USED FOR SPECIFICATION PURPOSES**