



CLAYBURN INDUSTRIES LTD.

33765 PINE STREET
ABBOTSFORD, BC
CANADA V2S 5C1
PHONE: (604) 859-5288
FAX: (604) 859-0424

TECHNICAL DATA

CLAYBURN GUN 26

CLAYBURN GUN 26 is a high strength, low iron, easy to gun mix for use up to 2600°F. It has low rebound and is resistant to moderate abrasion as found in ash hoppers and duct work. CLAYBURN GUN 26 has minimal shrinkage to resist cracking, giving a true monolithic lining.

SERVICE TEMPERATURE:	2600°F
MATERIAL REQUIRED FOR ESTIMATING:	128 lbs./cu. ft.
WATER REQUIRED:	Add at Nozzle

TYPICAL CHEMICAL ANALYSIS (Calcined Basis)

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	MgO	CaO	Alkalies	Other
48.2	41.4	0.8	1.7	0.1	5.5	0.1	2.0

TYPICAL PHYSICAL PROPERTIES

Prefired to °F	Modulus of Rupture, psi	Cold Crushing Strength, psi	Linear Change %
250	723	4,100	Nil
1500	650	2,750	-0.4
2500	1250	3,900	+0.8

124620 - 3/13/03

The data represents typical average results obtained by testing under ASTM or other acceptable procedures as required. They are subject to normal variations and should not be used for specifications.