



CLAYBURN INDUSTRIES LTD.

33765 PINE STREET
ABBOTSFORD, BC
CANADA V2S 5C1
PHONE: (604) 859-5288
FAX: (604) 859-0424



THERMAL CONDUCTIVITIES

DENSE FIREBRICK

Thermal Conductivity $\text{btu}/\text{ft}^2\text{hr}^0\text{F}/\text{in}$

<u>Mean Temperature</u>	<u>752⁰F</u>	<u>1472⁰F</u>	<u>2192⁰F</u>
CB 85D	14.9	14.6	17.0
CB 70D	10.3	10.0	10.6
CB 60LC	10.3	10.0	10.6
Super D	7.5	8.1	9.2
Skagit X	7.5	8.1	9.2.
Clayburn S	7.5	8.1	9.2

**ALL DATA SUBJECT TO REASONABLE DEVIATION AND THEREFORE
SHOULD NOT BE USED FOR SPECIFICATION PURPOSES**