



CLAYBURN INDUSTRIES LTD.

33765 PINE STREET
ABBOTSFORD, BC
CANADA V2S 5C1
PHONE: (604) 859-5288
FAX: (604) 859-0424



TECHNICAL DATA - TYPICAL

#686 DEEP RED CHAMPHERED PAVERS

Compressive Strength (Avg):	7,000 – 10,000 psi
Hot Water Absorption:	6.5 – 8.5%
Cold Water Absorption:	4.5 – 6.5%
Saturation Coefficient:	0.65 – 0.75
Efflorescence	Nil
ASTM Grade	SX

This product meets the requirements of ASTM C902.

June 2007

**ALL DATA SUBJECT TO REASONABLE DEVIATION AND THEREFORE
SHOULD NOT BE USED FOR SPECIFICATION PURPOSES**