



CLAYBURN INDUSTRIES LTD.

33765 PINE STREET
 ABBOTSFORD, BC
 CANADA V2S 5C1
 PHONE: (604) 859-5288
 FAX: (604) 859-0424



TECHNICAL DATA - TYPICAL
 INSULATING CASTABLES
THERMOLITE 22GES

(Gunned Data)

Classification	An extra strength lightweight 2200°F insulating castable suitable for gunning applications		
Service Limit	2200°F		(1205°C)
Dry Weight Required to Place 1 cu. ft. (m ³)	65 lbs		(1040 Kg)
<u>Linear Change on Heating</u>			
230°F	(110°C)	Nil %	
1500°F	(816°C)	-0.2 to -0.8%	
2100°F	(1149°C)	-1.0 to -1.5%	
<u>Cold Crushing Strength</u>			
230°F	(110°C)	900-1300 lbs/in ²	(6.2-9.0 MPa)
1500°F	(816°C)	700-1000 lbs/in ²	(4.8-6.9 MPa)
<u>Thermal Conductivity (Mean Temp)</u>			
400°F	(204°C)	<u>Btu/ft²•Hr•°F/in</u>	<u>W/mK</u>
800°F	(427°C)	2.07	0.30
1200°F	(649°C)	2.20	0.32
		2.37	0.34
<u>Chemical Analysis</u>			
Silica	SiO ₂	37.8%	
Alumina	Al ₂ O ₃	36.2%	
Iron	Fe ₂ O ₃	2.7%	
ASTM Designation	C401 Class "P"		

APR 09

**ALL DATA SUBJECT TO REASONABLE DEVIATION AND THEREFORE
 SHOULD NOT BE USED FOR SPECIFICATION PURPOSES**