



CLAYBURN INDUSTRIES LTD.

33765 PINE STREET
ABBOTSFORD, BC
CANADA V2S 5C1
PHONE: (604) 859-5288
FAX: (604) 859-0424



TECHNICAL DATA - TYPICAL

REFRACTORY MORTAR

CLAYBURN BEDDING MIX

HEAT SETTING

Classification	A dry refractory material with excellent resistance to cryolite suitable as a sweeping mortar or bedding material for aluminum pot-line service.	
Particle Size	85% passing 28 mesh (Tyler)	
Typical Screen Analysis	+28 mesh 15% -28 +65 mesh 40% -65 mesh 45%	
<u>Chemical Analysis</u>		
Silica	SiO ₂	59-64%
Alumina	Al ₂ O ₃	23-29%

JUN 07

**ALL DATA SUBJECT TO REASONABLE DEVIATION AND THEREFORE
SHOULD NOT BE USED FOR SPECIFICATION PURPOSES**