



**CLAYBURN INDUSTRIES LTD.**

33765 PINE STREET  
ABBOTSFORD, BC  
CANADA V2S 5C1  
PHONE: (604) 859-5288  
FAX: (604) 859-0424



## TECHNICAL DATA - TYPICAL

### REFRACTORY MORTAR

#### *FIRECLAY P*

#### *HEAT SETTING*

Classification	A dry refractory material with excellent resistance to cryolite suitable as a mortar or bedding material for aluminum pot-line service	
Particle Size	85% passing 28 mesh (Tyler)	
Typical Screen Analysis	+28 mesh 15% -28 +65 mesh 40% -65 mesh 45%	
<u>Chemical Analysis</u>		
Silica	SiO <sub>2</sub>	59-64%
Alumina	Al <sub>2</sub> O <sub>3</sub>	23-29%

JUN 07

**ALL DATA SUBJECT TO REASONABLE DEVIATION AND THEREFORE  
SHOULD NOT BE USED FOR SPECIFICATION PURPOSES**