



CLAYBURN INDUSTRIES LTD.

33765 PINE STREET
ABBOTSFORD, BC
CANADA V2S 5C1
PHONE: (604) 859-5288
FAX: (604) 859-0424



TECHNICAL DATA - TYPICAL

REFRACTORY MORTAR

SKAGIT FIRECLAY (DRY)

HEAT SETTING

| | |
|---------------------|--|
| Classification | A high duty heat setting refractory mortar |
| Service Temperature | 3100°F (1705°C) |
| Particle Size | 95% passing 28 mesh (Tyler) |

Chemical Analysis

| | | |
|---------|--------------------------------|----------|
| Silica | SiO ₂ | 51-55% |
| Alumina | Al ₂ O ₃ | 25-29% |
| Iron | Fe ₂ O ₃ | 2.6-3.0% |