



CLAYBURN INDUSTRIES LTD.

33765 PINE STREET
ABBOTSFORD, BC
CANADA V2S 5C1
PHONE: (604) 859-5288
FAX: (604) 859-0424

TECHNICAL DATA

CLAYBURN PLASTIC 75 SIC

CLAYBURN PLASTIC 75 SIC is a very high silicon carbide, phosphate bonded plastic. It was specifically developed for reducing conditions on the studded water tube walls of boilers. The high silicon carbide content gives CLAYBURN PLASTIC 75 SIC very high thermal conductivity and slag resistance.

SERVICE TEMPERATURE: 3100°F
MATERIAL REQUIRED FOR ESTIMATING: 168 lbs./cu. ft.

TYPICAL CHEMICAL ANALYSIS (Reducing Conditions)

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	MgO	CaO	SiC	Alkalies	P ₂ O ₅
16.8	4.9	0.3	0.1	0.1	0.0	73.9	0.2	3.4

TYPICAL PHYSICAL PROPERTIES (Reducing conditions above 250°F)

Prefired to °F	Modulus of Rupture, psi	Cold Crushing Strength, psi	Linear Change %
250	863	2,211	-0.4
2000	1379	2,897	+0.3

202420 - 04/19/99